

EPOXONIC®
EX 3525

**Toughened 2-Part-Adhesive
for Automotive Engineering,
Microelectronics, and Electrical Engineering**

EPOXONIC® EX 3525 is a solvent-free 2-part adhesive based on epoxy resin.

Main characteristics:

Chemical resistance
Low viscosity
Toughness
Good adhesion to plastics

Application:

EPOXONIC® EX 3525 is especially suited for low stress bonding of substrates with different thermal expansion (e.g. polycarbonate/glass-composites).

Properties:

Specific values measured by standard test specimen at 23 °C, cured 2 h / 80 °C.

Operating temperature	-40 °C to +150 °C; depending on the application, other limits may be reasonable	
Colour	colourless, opaque	
Shore hardness	80 Shore D	DIN EN ISO 868
Density	1.1 g/cm ³	DIN EN ISO 1183-1
Glass transition temperature (DSC)	85 – 95 °C	DIN EN ISO 11357
Shear strength on		EPOXONIC PV 29
Aluminum	50 MPa	
PC	30 MPa	
PPS	28 MPa	
PA 6.6	27 MPa	
Bending strength	90 MPa	DIN EN ISO 178
E-modulus	2,200 MPa	DIN EN ISO 178
Outer fibre strain at break	12 %	DIN EN ISO 178

Processing:

Mix ratio	Part A : Part B = 100 : 25 parts by weight	
Viscosity cone/plate viscometer		DIN 53019
	25 °C	10,000 – 15,000 mPas (Part A)
	25 °C	300 – 500 mPas (Part B)
	25 °C	2,500 – 4,500 mPas (Mixture A + B)
Pot life	25 °C	approx. 1 h (time to double viscosity)
Method of application	e.g. dispenser	
Cure schedule	e.g. 2 h / 80 °C Optimum cure schedules have to be determined by the specific application.	

Storage:

The shelf life of EPOXONIC® EX 3525 Part A and part B is 12 months at temperatures < 25 °C when stored in tightly closed, original containers.

Partly emptied containers should be tightly closed immediately after use.

Packaging:

EPOXONIC® EX 3525 Part A is delivered in metal cans. The Part B is delivered in cans with a pour spout.

Other packaging options are available upon request.

Health and Safety:

Recommended industrial hygiene procedures should always be followed when handling this product. Please refer to the corresponding Material Safety Data Sheet for details.

Quality Assurance:

If required EPOXONIC® EX 3525 will be supplied with a Certificate of Analysis.

Disclaimer:

All information herein is based on the present state of knowledge and believed to be reliable. Any suggestions or recommendations are made without liability on our part since we shall have no control over the use of our product. Buyers and users should make their own assessment of this product under their own conditions and for their own requirements.